



PTFE E-Carbon Härte 60 Shore D schwarz

PTFE E-Carbon hardness 60 shore D black

Composition % weight \pm 1:

Virgin PTFE + Carbon Fillers + Additives

Mechanische, physikalische und thermische Eigenschaften

Mechanical, physical and thermal properties

Eigenschaften properties	Bedingung condition	Norm standard	Einheit unit			
Farbe colour				schwarz black		schwarz black
Dichte/Spezifisches Gewicht density/specific gravity	23°C	DIN 53 479	kg/m ³	2130	g/cm ³	2,13
Härte hardness	23°C	ISO 868	shore D	60 \pm 3	shore D	60 \pm 3
Kugeldruckhärte Ball indentation hardness	23°C	DIN 53 456 H135/30	MPa	\geq 34	psi	\geq 4930
Reißfestigkeit tensile strength	23°C	ASTM D 4745-79	MPa	\geq 29	psi	\geq 4206
Reißdehnung elongation at break	23°C	ASTM D 4745-79	%	\geq 282	%	\geq 282
Druckfestigkeit compressive strength	23°C	DIN 53 455	MPa		psi	
Wärmeleitfähigkeit thermal conductivity	23°C	DIN 52 612	$\frac{J \times 10^3}{m \times h \times K}$	3,5	$\frac{J \times 10^3}{m \times h \times K}$	3,5
Linearer Wärmeausdehnungs- koeffizient coefficient of thermal expansion	25°C–200°C		K ⁻¹ x 10 ⁻⁵	10,9	K ⁻¹ x 10 ⁻⁵	10,9
Gleitreibungskoeffizient Coefficient of friction	*		μ	0,18	μ	0,18
Min. Einsatztemperatur minimum service temperature			°C	-200	°F	-328
Max. Einsatztemperatur maximum service temperature			°C	260	°F	500
E-Modul Zug young's modulus		DIN 53 457	MPa		psi	
* Gleitreibung im Trockenlauf gegen Stahl 16MnCr5: v=0,6 m/s; p=0,05 MPa; t=5h dynamic coefficient of friction, dry, Steel 16MnCr5: v=0,6 m/s; p=0,05 MPa; t=5h						

Chemical Properties

Filled PTFE

Resistant to: almost all chemicals

Not resistant to: halogenides, elemental fluorine, CF₃, molten alkali metals

Detailed information concerning chemical resistance see RDA Chemical Resistance Guide